

**SCHEDA TECNICA**  
*Data Sheet***ALR50 - ALLUMINIO OSSIDO R 50**  
*ALR50 - ALLUMINIUM OXIDE R 50*Umidità media / massima: 0.1% / 0.5%  
*moisture med/max*

<b>Analisi chimica</b> <i>chemical analysis</i>	<b>Min</b> <i>Min</i>	<b>Tipica</b> <i>typical</i>	<b>Max</b> <i>Max</i>
Al <sub>2</sub> O <sub>3</sub>		99.3 %	
SiO <sub>2</sub>			0.1 %
Fe <sub>2</sub> O <sub>3</sub>			0.1 %
CaO			0.05 %
P.F.			0.50 %

**Granulometria**  
*particle size*

&lt; 125 µm 95 %

**Composizione mineralogica**  
*Mineralogical composition*Alfa allumina 60 (+/- 20)  
*Alpha alumina***Altre caratteristiche**  
*Other informations*BET 10 (+/-4) m<sup>2</sup>/g  
D50 80 µm**Firma:**  
*Signature:*

Ed. 5 del 11-06-2013

La presente annulla e sostituisce le precedenti  
*The present act cancels and overrides the previous*

Pag.nr.

**1**