

**SCHEMA TECNICA**  
*Data Sheet*
**ARM1E - CAOLINO MACINATO**  
 ARM1E -

 Umidità media / massima: 2.5% / 4%  
*moisture med/max*

<b>Analisi chimica</b> <i>chemical analysis</i>	<b>Min</b> <i>Min</i>	<b>Tipica</b> <i>typical</i>	<b>Max</b> <i>Max</i>
SiO <sub>2</sub>		78.50 %	
Al <sub>2</sub> O <sub>3</sub>	14.8 %	15.80 %	
Fe <sub>2</sub> O <sub>3</sub>			1.00 %
TiO <sub>2</sub>		1.40 %	1.60 %
P.F.		4.30 %	4.80 %

<b>Granulometria</b> <i>particle size</i>			
> 60 µm		8 %	
> 45 µm		12.5 %	

<b>Composizione mineralogica</b> <i>Mineralogical composition</i>			
Caolinite <i>Kaolinite</i>		30 %	
Illite <i>Illite</i>		15 %	
Quarzo <i>Quartz</i>		50 %	
Altri		5 %	

<b>Altre caratteristiche</b> <i>Other informations</i>			
Peso specifico apparente a caduta <i>Bulk density</i>		0.6 g/cm <sup>3</sup>	

**Firma:**  
*Signature:*


Ed. 2 del 10-12-2015

 La presente annulla e sostituisce le precedenti  
*The present act cancels and overrides the previous*

Pag.nr.

**1**