

SCHEMA TECNICA
Data Sheet
ARM1E - CAOLINO MACINATO
ARM1E - MILLED KAOLIN

 Umidità media / massima: 2.5% / 4%
moisture med/max

Analisi chimica <i>chemical analysis</i>	Min <i>Min</i>	Tipica <i>typical</i>	Max <i>Max</i>
SiO ₂		78.50 %	
Al ₂ O ₃	14.8 %	15.80 %	
Fe ₂ O ₃			1.00 %
TiO ₂		1.40 %	1.60 %
P.F.		4.30 %	4.80 %

Granulometria <i>particle size</i>			
> 60 µm		8 %	
> 45 µm		12.5 %	

Composizione mineralogica <i>Mineralogical composition</i>			
Caolinite <i>Kaolinite</i>		30 %	
Illite <i>Illite</i>		15 %	
Quarzo <i>Quartz</i>		50 %	
Altri		5 %	

Altre caratteristiche <i>Other informations</i>			
Peso specifico apparente a caduta <i>Bulk density</i>		0.6 g/cm ³	

Firma:
Signature:


Ed. 2 del 10-12-2015

 La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1