

SCHEDA TECNICA
Data Sheet
ARM90 - ARGILLA MACINATA
 ARM90 -

 Umidità media / massima: 2.5% / 4.0%
moisture med/max

Analisi chimica <i>chemical analysis</i>	Min <i>Min</i>	Tipica <i>typical</i>	Max <i>Max</i>
SiO ₂		66,0 %	70,0 %
Al ₂ O ₃	19,5 %	21,0 %	
Fe ₂ O ₃		0,87 %	1,0 %
TiO ₂		1,20 %	1,60 %
CaO		0,14 %	
MgO		0,20 %	
Na ₂ O		0,20 %	
K ₂ O		1,35 %	
P.F.		7,00 %	

Granulometria
particle size

> 60 µm 8 %

Composizione mineralogica
Mineralogical composition

Illite <i>Illite</i>	10,0 %
Caolinite <i>Kaolinite</i>	51,0 %
Quarzo <i>Quartz</i>	34,0 %
Altri <i>Others</i>	5,0 %

Firma:
Signature:


Ed. 6 del 15-07-2015

 La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1