

SCHEDA TECNICA
Data Sheet
ARMK3 - ARGILLA
ARMK3 - CLAY

Umidità media / massima: 2 % / 4 %

moisture med/max

Analisi chimica <i>chemical analysis</i>	Min <i>Min</i>	Tipica <i>typical</i>	Max <i>Max</i>
SiO ₂		60,2 %	64,0 %
Al ₂ O ₃	26,0 %	27,7 %	
Fe ₂ O ₃		0,72 %	1,0 %
TiO ₂		0,79 %	1,10 %
CaO		0,09 %	
MgO		0,30 %	
Na ₂ O		0,16 %	
K ₂ O		0,63 %	1,10 %
P.F.		9,32 %	

Granulometria
particle size

> 45 µm	1,5 %
---------	-------

Composizione mineralogica
Mineralogical composition

Illite	8,2 %
Caolinite	60,6 %
Quarzo	28,8 %
Goethite	0,2 %
Feldspato	1,2 %
Anatasio	0,2 %
Altri	0,9 %

Firma:
Signature:


Ed. 1 del 04-09-2018

 La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1