

SCHEDA TECNICA
Data Sheet
ARP395 - ARGILLA
ARP395 - CLAY

Umidità media / massima: 14% / 16 %

moisture med/max

Analisi chimica <i>chemical analysis</i>	Min <i>Min</i>	Tipica <i>typical</i>	Max <i>Max</i>
SiO ₂		53.84 %	
Al ₂ O ₃	26 %	31.44 %	
Fe ₂ O ₃		0.79 %	1,10 %
TiO ₂		1.18 %	1,35 %
CaO		0.23 %	
MgO		0.11 %	
Na ₂ O		0.11 %	
K ₂ O		0.95 %	
P.F.		10.99 %	

Composizione mineralogica
Mineralogical composition

Illite <i>Illite</i>	8 %
Caolinite <i>Kaolinite</i>	77 %
Quarzo <i>Quartz</i>	12 %
Altri <i>Others</i>	3 %

Firma:
Signature:


Ed. 2 del 10-03-2014

 La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1