

SCHEDA TECNICA
Data Sheet
BFLS710 - BALCOFLUX 6040
BFLS710 -

Fondente , correttore impasto liquido

Glazing agent

Umidità media : 35 %

UMIDITAMED

| Analisi chimica <i>chemical analysis</i> | Min <i>Min</i> | Tipica <i>typical</i> | Max <i>Max</i> |
|--|--------------------------|---------------------------------|--------------------------|
| SiO ₂ | | 67.2 % | |
| Al ₂ O ₃ | | 12.2 % | |
| Fe ₂ O ₃ | | 0.09 % | 0.10 % |
| TiO ₂ | | 0.05 % | 0.10 % |
| CaO | | 11.4 % | |
| MgO | | 0.20 % | |
| Na ₂ O | | 0.57 % | |
| K ₂ O | | 0.20 % | |
| ZR02 | 5.00 % | 5.10 % | |
| LIO2 | 2.25 % | 2.50 % | |
| LOI | | 0.49 % | |

Granulometria
particle size

Residuo 45 micron 1.00 % max

Firma:
Signature:


Ed. 1 del 25-07-2018

 La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1