

**SCHEMA TECNICA***Data Sheet***BXT82S01 - BAUXITE CALCINATA 82%**  
*BXT82S01 - 82% CALCINATED BAUXITE*

Umidità massima: 0.5%

*Moisture max*

<b>Analisi chimica</b> <i>chemical analysis</i>	<b>Min</b> <i>Min</i>	<b>Tipica</b> <i>typical</i>	<b>Max</b> <i>Max</i>
SiO <sub>2</sub>			11.00 %
Al <sub>2</sub> O <sub>3</sub>	82.00 %		
Fe <sub>2</sub> O <sub>3</sub>			3.00 %
TiO <sub>2</sub>			4.50 %

**Granulometria**  
*particle size*

- 0 - 1 mm

**Altre caratteristiche**  
*Other informations*peso specifico apparente 2.65 min. g/cm<sup>3</sup>  
*Bulk density***Firma:**  
*Signature:*

Ed. 1 del 10-06-2015

La presente annulla e sostituisce le precedenti  
*The present act cancels and overrides the previous*

Pag.nr.

**1**