

SCHEMA TECNICA*Data Sheet***BXT82S01 - BAUXITE CALCINATA 82%**
BXT82S01 - 82% CALCINATED BAUXITE

Umidità massima: 0.5%

Moisture max

Analisi chimica <i>chemical analysis</i>	Min <i>Min</i>	Tipica <i>typical</i>	Max <i>Max</i>
SiO ₂			11.00 %
Al ₂ O ₃	82.00 %		
Fe ₂ O ₃			3.00 %
TiO ₂			4.50 %

Granulometria
particle size

- 0 - 1 mm

Altre caratteristiche
*Other informations*peso specifico apparente 2.65 min. g/cm³
*Bulk density***Firma:**
Signature:

Ed. 1 del 10-06-2015

La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1