

**SCHEDA TECNICA**  
*Data Sheet***BXT8501 - BAUXITE CALCINATA 85%**  
*BXT8501 - 85% CALCINED BAUXITE*Umidità massima: 0.5%  
*Moisture max*

<b>Analisi chimica</b> <i>chemical analysis</i>	<b>Min</b> <i>Min</i>	<b>Tipica</b> <i>typical</i>	<b>Max</b> <i>Max</i>
SiO <sub>2</sub>			7.50 %
Al <sub>2</sub> O <sub>3</sub>	85.00 %		
Fe <sub>2</sub> O <sub>3</sub>			2.00 %
TiO <sub>2</sub>			4.00 %
Na <sub>2</sub> O+K <sub>2</sub> O			0.50 %
MgO + CaO			0.50 %

**Granulometria**  
*particle size*

- 0 - 1 mm

**Altre caratteristiche**  
*Other informations*densità apparente 3.05 min. g/cm<sup>3</sup>  
*Bulk density***Firma:**  
*Signature:*

Ed. 1 del 10-06-2015

La presente annulla e sostituisce le precedenti  
*The present act cancels and overrides the previous*

Pag.nr.

**1**