

**SCHEMA TECNICA**  
*Data Sheet*

**BXT8513 - BAUXITE CALCINATA 85%**  
*BXT8513 - 85% CALCINATED BAUXITE*


Umidità massima: 0.5%  
*Moisture max*

<b>Analisi chimica</b> <i>chemical analysis</i>	<b>Min</b> <i>Min</i>	<b>Tipica</b> <i>typical</i>	<b>Max</b> <i>Max</i>
SiO <sub>2</sub>			7.50 %
Al <sub>2</sub> O <sub>3</sub>	85.00 %		
Fe <sub>2</sub> O <sub>3</sub>			2.00 %
TiO <sub>2</sub>			4.00 %
Na <sub>2</sub> O+K <sub>2</sub> O			0.50 %
MgO + CaO			0.50 %

<b>Granulometria</b> <i>particle size</i>
-
1 - 3 mm

<b>Altre caratteristiche</b> <i>Other informations</i>	
densità apparente <i>bulk density</i>	3.05 min g/cm <sup>3</sup>

**Firma:**  
*Signature:*



Ed. 1 del 10-06-2015

La presente annulla e sostituisce le precedenti  
*The present act cancels and overrides the previous*

Pag.nr. **1**