

SCHEMA TECNICA
Data Sheet

BXT8536 - BAUXITE CALCINATA 85%
BXT8536 - 85% CALCINATED BAUXITE

Umidità massima: 0.5%
Moisture max

Analisi chimica <i>chemical analysis</i>	Min <i>Min</i>	Tipica <i>typical</i>	Max <i>Max</i>
SiO ₂			7.50 %
Al ₂ O ₃	85.00 %		
Fe ₂ O ₃			2.00 %
TiO ₂			4.00 %
Na ₂ O+K ₂ O			0.50 %
MgO + CaO			0.50 %

Granulometria
particle size

- 3 - 6 mm

Altre caratteristiche
Other informations

densità apparente 3.05 min g/cm³
bulk density

Firma:
Signature:



Ed. 1 del 10-06-2015

La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr. **1**