

SCHEDA TECNICA
Data Sheet
CAPOKA - CAOLINO
CAPOKA - Kaolin powder

Analisi chimica <i>chemical analysis</i>	Min <i>Min</i>	Tipica <i>typical</i>	Max <i>Max</i>
SiO ₂		52.3 %	
Al ₂ O ₃		34.0 %	
Fe ₂ O ₃		0.40 %	
TiO ₂		0.17 %	
CaO		0.17 %	
K ₂ O		0.28 %	
MgO		0.25 %	
Na ₂ O		0.01 %	
L.O.I.		12.3 %	
F		230 ppm	

Granulometria
particle size

> 45 µm	0.05 %
< 2 mm	70 %
D50	0.90 µm

Composizione mineralogica
Mineralogical composition

Caolinite <i>Kaolinite</i>	83 %
Quarzo <i>Quartz</i>	13 %
Illite/Montmorillonite <i>Illite / Montmorillonite</i>	4 %

Firma:
Signature:


Ed. 1 del 14-07-2017

 La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1