

**SCHEDA TECNICA****CAPOKA - CAOLINO****Analisi chimica****Min****Tipica****Max**

SiO <sub>2</sub>		52.3 %	
Al <sub>2</sub> O <sub>3</sub>		34.0 %	
Fe <sub>2</sub> O <sub>3</sub>		0.40 %	
TiO <sub>2</sub>		0.17 %	
CaO		0.17 %	
K <sub>2</sub> O		0.28 %	
MgO		0.25 %	
Na <sub>2</sub> O		0.01 %	
L.O.I.		12.3 %	
F		230 ppm	

**Granulometria**

> 45 µm		0.05 %	
< 2 mm		70 %	
D50		0.90 µm	

**Composizione mineralogica**

Caolinite		83 %	
Quarzo		13 %	
Illite/Montmorillonite		4 %	

**Firma:****Ed. 1 del 14-07-2017**

La presente annulla e sostituisce le precedenti

Pag.nr.

**1**