

**SCHEDA TECNICA**  
*Data Sheet*

**CRAKTB - CORINDONE**  
*CRAKTB -*

<b>Analisi chimica</b> <i>chemical analysis</i>	<b>Min</b> <i>Min</i>	<b>Tipica</b> <i>typical</i>	<b>Max</b> <i>Max</i>
Al <sub>2</sub> O <sub>3</sub>	99.50 %		
Fe <sub>2</sub> O <sub>3</sub>			0.05 %
SiO <sub>2</sub>			0.05 %
Na <sub>2</sub> O			0.40 %

**Granulometria**  
*particle size*

GRANE DISPONIBILI: (scala FEPA standard)  
AVAILABLE SIZE (FEPA standard scale)

F100  
F150  
F220  
F240

**Altre caratteristiche**  
*Other informations*

PESO SPECIFICO  
BULK DENSITY

F100	1,68 - 1,78 g/cm <sup>3</sup>
F150	1,62 - 1,72 g/cm <sup>3</sup>
F220	1,57 - 1,67 g/cm <sup>3</sup>
F240	1,54 - 1,64 g/cm <sup>3</sup>

Temperatura di fusione  
Melting point

2050 °C

Firma:  
Signature:



Ed. 1 del 04-04-2016

La presente annulla e sostituisce le precedenti  
The present act cancels and overrides the previous

Pag.nr.

**1**