

**SCHEDA TECNICA**
**FLG90 - FLUORITE 90%**

Umidità massima: 1%

<b>Analisi chimica</b>	<b>Min</b>	<b>Tipica</b>	<b>Max</b>
CaF <sub>2</sub>	88.0 %	90.0 %	
SiO <sub>2</sub>		4.8 %	7.5 %
Fe <sub>2</sub> O <sub>3</sub>		0.08 %	0.16 %
CaCO <sub>3</sub>		2.6 %	3.0 %
Al <sub>2</sub> O <sub>3</sub>		0.021 %	0.32 %
P <sub>2</sub> O <sub>5</sub>			0.05 %
BaSO <sub>4</sub>			0.015 %
MgO			0.02 %
S		0.018 %	0.018 %
P		0.021 %	0.026 %
Pb		0.001 %	0.001 %
As			0.018 %
Sn			0.03 %
ZnO			3 ppm

**Granulometria**

> 300	0.5 µm
> 150	18.0 µm
> 105	30.0 µm
> 75	39.0 µm
> 45	56.0 µm

Firma:



Ed. 2 del 25-07-2012

La presente annulla e sostituisce le precedenti

Pag.nr.

1