

**SCHEDA TECNICA**
*Data Sheet*
**FSK700 - FELDSPATO**
*FSK700 - FELDSPAR*

Umidità massima: 1%

*Moisture max*

<b>Analisi chimica</b> <i>chemical analysis</i>	<b>Min</b> <i>Min</i>	<b>Tipica</b> <i>typical</i>	<b>Max</b> <i>Max</i>
SiO <sub>2</sub>		67.90 %	
Al <sub>2</sub> O <sub>3</sub>		16.80 %	
Fe <sub>2</sub> O <sub>3</sub>		0.13 %	
TiO <sub>2</sub>		0.51 %	
CaO		0.02 %	
MgO		0.03 %	
Na <sub>2</sub> O		0.55 %	
K <sub>2</sub> O		12.80 %	
BaO		0.28 %	
P <sub>2</sub> O <sub>5</sub>		0.08 %	
P.F.		0.90 %	

**Granulometria**  
*particle size*

> 500 μm	0.1 %
200 - 500 μm	0.7 %
100 - 200 μm	4 %
63 - 100 μm	23 %
40 - 63 μm	32 %
< 40 μm	40 %

**Composizione mineralogica**  
*Mineralogical composition*

Feldspato potassico	75 %
Feldspato sodico	5 %
Quarzo	13 %
Parte argillosa	7 %

**Altre caratteristiche**  
*Other informations*

Peso specifico	900 Kg/m <sup>3</sup>
----------------	-----------------------

**Firma:**
*Signature:*


Ed. 1 del 25-06-2009

 La presente annulla e sostituisce le precedenti  
*The present act cancels and overrides the previous*

Pag.nr.

**1**