

SCHEDA TECNICA**FSKM2 - FELDSPATO FS900 S**

Umidità massima: 18%

Analisi chimica	Min	Tipica	Max
SiO ₂	65.5 %	66.4 %	69.1 %
Al ₂ O ₃	17.0 %	17.50 %	18.0 %
Fe ₂ O ₃		0.034 %	0.038 %
TiO ₂		0.023 %	
CaO		0.03 %	0.04 %
MgO		0.01 %	
Na ₂ O	0.7 %	0.81 %	0.9 %
K ₂ O	13.9 %	14.40 %	14.8 %
P ₂ O ₅		0.07 %	
BaO		0.31 %	
P.F.	0.1 %	0.25 %	0.3 %

Granulometria

> 0.5 mm	0.2 %
< 0.04 mm	20 - 44.4 %

Composizione mineralogica

Feldspato totale	92 %
Feldspato Sodico	6.6 %
Feldspato Potassico	85.4 %
Quarzo	5 %
Argilla	2 %

Firma:



Ed. 2 del 15-12-2016

La presente annulla e sostituisce le precedenti

Pag.nr.

1