

SCHEDA TECNICA
Data Sheet
FSKM8 - FELDSPATO FS900 L/M8
FSKM8 - FS900 L/M8 FELDSPAR

 Umidità massima: 1.0 %
Moisture max

Analisi chimica <i>chemical analysis</i>	Min <i>Min</i>	Tipica <i>typical</i>	Max <i>Max</i>
SiO ₂	64.8 %		66.8 %
Al ₂ O ₃	17.0 %		18.5 %
Fe ₂ O ₃			0.05 %
TiO ₂			0.05 %
Na ₂ O		0.7 %	0.9 %
K ₂ O		14.3 %	15.0 %
P.F.		0.10 %	0.30 %

Granulometria
particle size

> 75 µm	3.0 %
> 75 µm	

Composizione mineralogica
Mineralogical composition

Feldspato totale <i>Total feldspar</i>	94 %
Feldspato Potassico <i>Potassium feldspar</i>	87 %
Feldspato sodico <i>Sodium feldspar</i>	7 %
Quarzo <i>Quartz</i>	4 %
Parte argillosa <i>Clay fraction</i>	2 %

Altre caratteristiche
Other informations

Peso specifico apparente <i>Bulk density</i>	1100 Kg/m ³
Peso specifico <i>True density</i>	2.6 g/cm ³
pH <i>pH</i>	4.0

Firma:
Signature:


Ed. 4 del 16-02-2017

 La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1