

SCHEMA TECNICA
Data Sheet**FSKNI - FELDSPATO NC-4**
FSKNI -Umidità media / massima: 0.2% / 1%
moisture med/max

| Analisi chimica chemical analysis | Min Min | Tipica typical | Max Max |
|---|-------------------|--------------------------|-------------------|
| SiO ₂ | 65.00 % | 68.2 % | 70.00 % |
| Al ₂ O ₃ | 18.00 % | 18.5 % | 20.60 % |
| Fe ₂ O ₃ | | 0.03 % | 0.10 % |
| TiO ₂ | | 0.04 % | 0.10 % |
| Na ₂ O | 6.00 % | 7.71 % | 9.00 % |
| K ₂ O | 3.00 % | 3.90 % | 4.30 % |
| P.F. | | | 0.18 % |

Granulometria
particle size

> 30 µm 9.0 %

Composizione mineralogica
Mineralogical composition

| | |
|------------------|------|
| Quarzo | 8 % |
| Albite | 65 % |
| Anortite | 5 % |
| Microcl./Ortocl. | 20 % |
| Caolinite | 1 % |
| Altri | 1 % |

Altre caratteristiche
Other informations

Ferro magnetico 1.5 %

Firma:
Signature:

Ed. 3 del 19-12-2017

La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1