

SCHEMA TECNICA
*Data Sheet***FSKNI - FELDSPATO NC-4**
*FSKNI - NC-4 FELDSPAR*Umidità media / massima: 0.2% / 1%
moisture med/max

Analisi chimica <i>chemical analysis</i>	Min <i>Min</i>	Tipica <i>typical</i>	Max <i>Max</i>
SiO ₂	65.00 %	68.2 %	70.00 %
Al ₂ O ₃	18.00 %	18.5 %	20.60 %
Fe ₂ O ₃		0.03 %	0.10 %
TiO ₂		0.04 %	0.10 %
Na ₂ O	6.00 %	7.71 %	9.00 %
K ₂ O	3.00 %	3.90 %	4.30 %
P.F.			0.18 %

Granulometria
particle size

> 30 µm 9.0 %

Composizione mineralogica
Mineralogical composition

Quarzo	8 %
Albite	65 %
Anortite	5 %
Microcl./Ortocl.	20 %
Caolinite	1 %
Altri	1 %

Altre caratteristiche
Other informations

Ferro magnetico 1.5 %

Firma:
Signature:

Ed. 3 del 19-12-2017

La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1