

SCHEDA TECNICA
Data Sheet
FSKNS - FELDSPATO NC4
 FSKNS -

 Umidità media / massima: 0.2 % / 1.5 %
moisture med/max

Analisi chimica <i>chemical analysis</i>	Min <i>Min</i>	Tipica <i>typical</i>	Max <i>Max</i>
SiO ₂	65.0 %	68.2 %	70.0 %
Al ₂ O ₃	18.0 %	18.5 %	20.6 %
Fe ₂ O ₃		0.03 %	0.04 %
TiO ₂		0.04 %	0.05 %
Na ₂ O	6.00 %	7.71 %	9.00 %
K ₂ O	3.00 %	3.90 %	4.30 %
P.F.			0.18 %

Granulometria
particle size

 RESIDUO A SECCO ALPINE
 DRY RESIDUE with ALPINE

> 300 µm	0.3 %
> 150	18.0 %

Composizione mineralogica
Mineralogical composition

Caolinite <i>Kaolinite</i>	1 %
Albite <i>Albite</i>	65 %
Microcl/Ortocl. <i>Microcl/Ortocl.</i>	20 %
Quarzo <i>Quartz</i>	8 %
Anortite <i>Anorthosite</i>	5 %
Altri <i>Others</i>	1 %

 Firma:
 Signature:



Ed. 2 del 14-09-2017

 La presente annulla e sostituisce le precedenti
 The present act cancels and overrides the previous

Pag.nr.

1