

**SCHEDA TECNICA**
*Data Sheet*
**FSKNS - FELDSPATO NC4**
*FSKNS - NC-4 FELDSPAR*

Umidità media / massima: 0.2 % / 1.5 %

*moisture med/max*

<b>Analisi chimica</b> <i>chemical analysis</i>	<b>Min</b> <i>Min</i>	<b>Tipica</b> <i>typical</i>	<b>Max</b> <i>Max</i>
SiO <sub>2</sub>	65.0 %	68.2 %	70.0 %
Al <sub>2</sub> O <sub>3</sub>	18.0 %	18.5 %	20.6 %
Fe <sub>2</sub> O <sub>3</sub>		0.03 %	0.04 %
TiO <sub>2</sub>		0.04 %	0.05 %
Na <sub>2</sub> O	6.00 %	7.71 %	9.00 %
K <sub>2</sub> O	3.00 %	3.90 %	4.30 %
P.F.			0.18 %

**Granulometria**
*particle size*

RESIDUO A SECCO ALPINE

*DRY RESIUDUE with ALPINE*

> 300 µm	0.3 %
> 150	18.0 %

**Composizione mineralogica**
*Mineralogical composition*

Caolinite <i>Kaolinite</i>	1 %
Albite <i>Albite</i>	65 %
Microcl/Ortocl. <i>Microcl/Ortocl.</i>	20 %
Quarzo <i>Quartz</i>	8 %
Anortite <i>Anorthosite</i>	5 %
Altri <i>Others</i>	1 %

**Firma:**
*Signature:*


Ed. 2 del 14-09-2017

 La presente annulla e sostituisce le precedenti  
*The present act cancels and overrides the previous*

Pag.nr.

**1**