

**SCHEDA TECNICA**  
*Data Sheet*
**NP270 - NAKAFLUX FELDSPATO**  
*NP270 -*

 Umidità massima: 050 %  
*Moisture max*

<b>Analisi chimica</b> <i>chemical analysis</i>	<b>Min</b> <i>Min</i>	<b>Tipica</b> <i>typical</i>	<b>Max</b> <i>Max</i>
SiO <sub>2</sub>		59.00 %	
Al <sub>2</sub> O <sub>3</sub>	22.20 %	23.00 %	
Fe <sub>2</sub> O <sub>3</sub>		0.09 %	0.11 %
TiO <sub>2</sub>		0.10 %	0.17 %
K <sub>2</sub> O	6.70 %	6.95 %	
CaO		0.38 %	
MgO		0.03 %	
Na <sub>2</sub> O	8.10 %	10.20 %	
P.F.		0.25 %	

<b>Granulometria</b> <i>particle size</i>	
> 75 µm	0.5 %
> 45 µm	5 %

<b>Composizione mineralogica</b> <i>Mineralogical composition</i>	
Albite <i>Albite</i>	53 %
Microclino <i>Microclino</i>	21 %
Nefelina <i>Nepheline</i>	26 %

**Firma:**  
*Signature:*


Ed. 5 del 14-11-2017

 La presente annulla e sostituisce le precedenti  
*The present act cancels and overrides the previous*

 Pag.nr. **1**