

SCHEMA TECNICA
Data Sheet

SOST - OSSIDO DI STAGNO
SOST - TIN OXIDE

Analisi chimica
chemical analysis

Min
Min

Tipica
typical

Max
Max

SnO ₂	99.80 %		
Pb			500 ppm
Sb			300 ppm
As			200 ppm
Fe			200 ppm
Al			200 ppm
Bi			200 ppm
Cu			100 ppm
Ni			50 ppm
Zn			50 ppm
Cd			20 ppm

Granulometria
particle size

LASER CILAS 930

D 10	0.3 μm
D 50	1.0 μm
D 90	2.62 μm

Altre caratteristiche
Other informations

Peso specifico <i>Specific weight</i>	6.95 g/cm ³
Superficie specifica (BET) <i>Specific surface (BET)</i>	5 m ² /g
Punto di fusione <i>Melting point</i>	> 1630 °C
Peso molecolare <i>Molecular weight</i>	151 g/mol

Firma:
Signature:



Ed. 5 del 18-03-2009

La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1