

**SCHEDA TECNICA**  
*Data Sheet*

**SOSTI - OSSIDO DI STAGNO**  
*SOSTI - TIN OXIDE*

<b>Analisi chimica</b> <i>chemical analysis</i>	<b>Min</b> <i>Min</i>	<b>Tipica</b> <i>typical</i>	<b>Max</b> <i>Max</i>
SnO <sub>2</sub>	99.85 %		
Pb			0.05 %
Sb			0.05 %
As			0.05 %
Fe			0.05 %
Mn			0.01 %
Bi			0.05 %
Cu			0.05 %
Ni			0.05 %
Co			0.05 %
Zn			0.01 %
Cd			0.01 %
Mg			0.01 %
Ag			0.01 %
In			0.05 %
Impurità max totali			0.15 %
<b>Granulometria</b> <i>particle size</i>			
LASER MALVERN			
D 10		0.37 µm	
D 50		1.60 µm	
D 90		4.50 µm	
<b>Altre caratteristiche</b> <i>Other informations</i>			
Peso specifico <i>Specific weight</i>		650 g/l	
Superficie specifica (BET) <i>Specific surface (BET)</i>		8 m <sup>2</sup> g <sup>-1</sup>	

**Firma:**  
*Signature:*



Ed. 7 del 18-10-2010

La presente annulla e sostituisce le precedenti  
*The present act cancels and overrides the previous*

Pag.nr.

**1**