

SCHEMA TECNICA**WWM400 - WOLLASTONITE MACINATA**

Umidità media : 0.5%

Analisi chimica	Min	Tipica	Max
SiO ₂	50.50 %		54.50 %
CaO	43.00 %		47.00 %
Fe ₂ O ₃	0.20 %		0.35 %
L.O.I.	0.10 %		1.00 %

Granulometria

MICROTRAC

D50 % 7.00 - 11.00 µm

RESIDUO A 325 Tyler Mesh < 99.88 %

Altre caratteristiche

Assorbimento Olio 22 -34 lbs/100lbs

Firma:



Ed. 3 del 06-09-2017

La presente annulla e sostituisce le precedenti

Pag.nr.

1