

SCHEDA TECNICA*Data Sheet***WWM400 - WOLLASTONITE MACINATA***WWM400 - MILLED WOLLASTONITE*

Umidità media : 0.5%

UMIDITAMED

Analisi chimica <i>chemical analysis</i>	Min <i>Min</i>	Tipica <i>typical</i>	Max <i>Max</i>
SiO ₂	50.50 %		54.50 %
CaO	43.00 %		47.00 %
Fe ₂ O ₃	0.20 %		0.35 %
L.O.I.	0.10 %		1.00 %

Granulometria*particle size*

MICROTRAC

D50 % 7.00 - 11.00 µm

RESIDUO A 325 Tyler Mesh

< 99.88 %

*RESIDUE AT 325 Tyler Mesh***Altre caratteristiche***Other informations*

Assorbimento Olio

22 -34 lbs/100lbs

*Oil absorbance***Firma:***Signature:*

Ed. 3 del 06-09-2017

La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1