

SCHEDA TECNICA
Data Sheet
ZMR9 - MICROZIR STANDARD
 ZMR9 -

 Umidità media / massima: 0.1% / 1.0%
moisture med/max

Analisi chimica <i>chemical analysis</i>	Min <i>Min</i>	Tipica <i>typical</i>	Max <i>Max</i>
ZrO ₂	62.0 %	65.0 %	
Fe ₂ O ₃			0.13 %
TiO ₂			0.20 %
Al ₂ O ₃			1.80 %
SiO ₂			35.3 %
LOI		0.70 %	

Granulometria
particle size

 LASER CILAS 930 E
 LASER with CILAS 930E

D50	1.88 μm
D90	5.29 μm
D medio <i>Average diameter</i>	2.46 μm

Altre caratteristiche
Other informations

Peso specifico minerale <i>Mineral true density</i>	4.6 g/cm ³
Durezza <i>Hardness</i>	7.5 Mohs
Punto di fusione <i>Melting point</i>	2200 °C

Firma:
Signature:


Ed. 6 del 05-03-2014

 La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1