

SCHEMA TECNICA*Data Sheet***ZMR9 - MICROZIR STANDARD***ZMR9 -*

Umidità media / massima: 0.1% / 1.0%

moisture med/max

Analisi chimica <i>chemical analysis</i>	Min <i>Min</i>	Tipica <i>typical</i>	Max <i>Max</i>
ZrO ₂	62.0 %	65.0 %	
Fe ₂ O ₃			0.13 %
TiO ₂			0.20 %
Al ₂ O ₃			1.80 %
SiO ₂			35.3 %
LOI		0.70 %	

Granulometria*particle size*

LASER CILAS 930 E

LASER with CILAS 930E

D50	1.88 μm
D90	5.29 μm
D medio	2.46 μm
<i>Average diameter</i>	

Altre caratteristiche*Other informations*

Peso specifico minerale	4.6 g/cm ³
<i>Mineral true density</i>	
Durezza	7.5 Mohs
<i>Hardness</i>	
Punto di fusione	2200 °C
<i>Melting point</i>	

Firma:*Signature:*

Ed. 6 del 05-03-2014

La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1