

**SCHEMA TECNICA**  
*Data Sheet***ZRSU - SABBIA DI ZIRCONIO**  
*ZRSU - ZIRCONIUM SAND*Umidità media / massima: 0.1% / 0.5 %  
*moisture med/max*

| <b>Analisi chimica</b><br><i>chemical analysis</i> | <b>Min</b><br><i>Min</i> | <b>Tipica</b><br><i>typical</i> | <b>Max</b><br><i>Max</i> |
|--|--------------------------|---------------------------------|--------------------------|
| ZrO <sub>2</sub> + HfO <sub>2</sub>                | 65.00 %                  | 65.40 %                         |                          |
| Fe <sub>2</sub> O <sub>3</sub>                     |                          | 0.068 %                         | 0.09 %                   |
| TiO <sub>2</sub>                                   |                          | 0.15 %                          | 0.30 %                   |
| Al <sub>2</sub> O <sub>3</sub>                     |                          | 0.21 %                          | 1.80 %                   |

**Granulometria**  
*particle size*Residuo a 325 µm  
*Residue at 325 µm* 5 %**Altre caratteristiche**  
*Other informations*Attività specifica di radionuclidi naturali  
*Specific activity of natural radionuclides* 2.8 - 4 kBq/Kg**Firma:**  
*Signature:*

Ed. 1 del 11-05-2015

La presente annulla e sostituisce le precedenti  
*The present act cancels and overrides the previous*

Pag.nr.

**1**