

**SCHEDA TECNICA**
**BFLS710 - BALCOFLUX 6040**

Fondente , correttore impasto liquido

Umidità media : 35 %

| <b>Analisi chimica</b>         | <b>Min</b> | <b>Tipica</b> | <b>Max</b> |
|--------------------------------|------------|---------------|------------|
| SiO <sub>2</sub>               |            | 67.2 %        |            |
| Al <sub>2</sub> O <sub>3</sub> |            | 12.2 %        |            |
| Fe <sub>2</sub> O <sub>3</sub> |            | 0.09 %        | 0.10 %     |
| TiO <sub>2</sub>               |            | 0.05 %        | 0.10 %     |
| CaO                            |            | 11.4 %        |            |
| MgO                            |            | 0.20 %        |            |
| Na <sub>2</sub> O              |            | 0.57 %        |            |
| K <sub>2</sub> O               |            | 0.20 %        |            |
| ZR02                           | 5.00 %     | 5.10 %        |            |
| LIO2                           | 2.25 %     | 2.50 %        |            |
| LOI                            |            | 0.49 %        |            |

**Granulometria**

Residuo 45 micron 1.00 % max

Firma:



Ed. 1 del 25-07-2018

La presente annulla e sostituisce le precedenti

Pag.nr.

**1**