

SCHEDA TECNICA
SCHEDA TECNICA**WWM325 - WOLLASTONITE MACINATA**
WWM325 -

Umidità massima: 0.5%

Umidità max:

Analisi chimica <i>Analisi chimica</i>	Min <i>Min</i>	Tipica <i>Tipica</i>	Max <i>Max</i>
SiO ₂	50.50 %		54.50 %
CaO	43.00 %		47.00 %
Fe ₂ O ₃	0.20 %		0.35 %
LOI	0.10 %		1.00 %

Granulometria
Granulometria

D50 (metodo CILAS 920)	6.00 - 9.00 µm
D50 (metodo Microtrac)	10.00 - 16.00 µm
< 325 Mesh	99.00 min. %

Firma:

Firma:



Ed. 2 del 03-06-2014

La presente annulla e sostituisce le precedenti
The present act cancels and overrides the previous

Pag.nr.

1