

SCHEDA TECNICA**WWM45 - WOLLASTONITE MACINATA**

Umidità massima: 0.5%

Analisi chimica	Min	Tipica	Max
SiO ₂	50.50 %		54.50 %
CaO	43.00 %		47.00 %
Fe ₂ O ₃	0.20 %		0.35 %
Pb			< 100 ppm
Cl		assente	
S		assente	
F		assente	
LOI	0.10 %		1.00 %

Granulometria

> 45 µm		3.5 %	
D50 (metodo CILAS 920)		12.5 - 19.50 µm	
D50 (metodo Microtrac)		15.5 - 22.50 µm	
< 200 Mesh		> 99.00 %	

Firma:



Ed. 2 del 03-06-2014

La presente annulla e sostituisce le precedenti

Pag.nr.

1